

Blue, Beige

Description:

Statfree B™ meets the minimum recommended worksurface requirement of ANSI/ESD S20.20 of <10E9 ohms. This extruded homogeneous vinyl dissipative material can be used with either side up. One side has a smooth surface which is easy-to-clean and maintain, and the other has a non-glare finish which makes it easier to identify small parts. Statfree B™ is easy to cut to configure to fit your requirements. The material is dimensionally stable with minimum shrinkage or curling.

Statfree B™ has excellent color stability, minimizing discoloration. The 0.100" thick is a better value, providing a longer life and is ideal for general purpose worksurface matting. The thinner 0.060" material is the economical choice, and is ideal for use on cafeteria-style trays.

Statfree B™ is manufactured without any ozone depleting substances, and in accordance with the Montreal Protocol.

Electrical Properties:

Property	Test Method	Value
RTG Resistance:	ESD S4.1	<10E9 Ohms
RTT Resistance:	ESD S4.1	<10E9 Ohms

Electrical Properties obtained by testing to industrial standards by an independent testing laboratory @ 100 Volts and 50% relative humidity unless otherwise specified. Complete text of the test report is available upon request.

Disclaimer:

All statements, technical data, and recommendations contained herein are based upon tests we believe to be reliable. However, the accuracy or completeness thereof is not guaranteed. The proper and correct applications of products and data is the responsibility of the user. Statements or recommendations not contained herein shall have no force or effect unless embodied in a written agreement signed by authorized officers of Desco Industries, Inc.

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

Specifications:

Construction:	Homogeneous extruded thermoplastic vinyl
Thickness:	0.100" (2.5mm) and 0.060" (1.5mm), nominal ±10%
Texture:*	One side smooth, one side embossed
Colors:*	Blue, Beige
Hardness:	80 shore A (ASTM D-2240)
Wear Resistance:	Negligible weight loss (750 cycles, Taber CS-17 Method)

*Color, texture, and gauge may vary between lots and mills

Grounding: This material must be properly grounded for optimum electrical performance. Ask for Technical Bulletin TB-2000 for mat grounding instructions.

Cleaning: For optimum electrical performance, surface must be cleaned regularly using an ESD mat cleaner. We suggest using our Reztore™ Surface & Mat Cleaner Item #10435 or Static-Wipes Item #10600. Do not use cleaners with silicone. Silicone buildup will create an insulative film on the surface.

RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Desco Industries Inc. letter on-line at Desco.com.

See reverse side for available mat and roll sizes

Limited Lifetime Warranty:

Desco warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Desco Limited Warranty.

Note: Since it does not have a conductive layer, Statfree B™ is not suitable for use with continuous monitors.



Made in America

STATFREE B™ MATERIAL, VINYL, DISSIPATIVE, HOMOGENEOUS, .100" & .060"

DESCO

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com
PHONE (909) 627-8178 FAX (909) 627-7449

DESCO EAST: 90 HUDSON RD, CANTON, MA 02021-1407
PHONE (781) 821-8370 FAX (781) 575-0172


MATERIAL STATFREE B™

DRAWING PM-78

DATE:
10/06

Item Number Reference For Statfree B™ Vinyl, Dissipative, Homogeneous

KITS



Mat Top Kit Item Numbers

SIZE	BEIGE	BLUE
24" x 36"	16201	16213
24" x 48"	16202	16214

Tolerances:

Width $\pm .250"$
Length $\pm .250"$ every 1 linear foot of running material.

Look for the Statfree® brand on Desco ESD matting. All Desco mat top kits are permanently marked for your protection and auditing purposes.

MAT TOP KIT INCLUDES



1 Benchmat, Statfree B™, size as specified
1 14213, common point ground kit

ROLL STOCK



Statfree B™
Is Also
Available In
Full
Rolls

0.100" (2.5mm) &
0.060" (1.5mm)
THICK ROLLS



Hardware is not included with rolls.

Roll Stock Item Numbers

SIZE	BEIGE	BLUE
0.100" x 24" x 40'	16250	
0.100" x 24" x 100'	16251	16261
0.100" x 30" x 40'	16255	16265
0.100" x 30" x 100'		16266
0.100" x 36" x 40'	16280	16282
0.100" x 36" x 100'		16267
0.100" x 48" x 40'	16281	16283
0.060" x 24" x 100'		16290
0.060" x 30" x 100'		16291
0.060" x 36" x 100'		16292
0.060" x 48" x 100'		16293

Grounding Intervals for ESD Mats

Sufficient ground cords should be used to reliably meet ANSI/ESD S20.20 Table 1 less than 1×10^9 ohms for worksurfaces. An industry recommendation has been that continuous runs of ESD matting should be grounded at ten-foot intervals to allow proper charge decay rates with each individual ESD mat should be grounded with ground snap located no further than five feet from either end.